Product Data Sheet: Natural Lime Mortar

9/09/2014

Pre mixed natural hydraulic lime and sand mortar. A general purpose mortar for building or pointing stone, brick and block: available in different strengths, sand gradings and colours.

General Information

Lime Green Natural mortar is a dry pre-mixed lime mortar made with St Astier pure and natural hydraulic lime and including pigments where required.

Three different sand textures are available:

SG (approx 1mm down) RG (approx 2mm down) CG (approx 3mm down)

- CHALK NATURIL.

Lime Green has a wide range of colour options. Product samples may be ordered.

Packaging

Available in 25 kg bags or sealed one tonne bulk bags. All colours and textures other than off white (CG20) are made to order. Please call for lead times.

Coverage

Repointing: 20kg m² stonework; 7kg m² brickwork.

I kg of dried product per brick, or 1.5 tonnes will produce I metre cubed of mortar.

Which Mortar?

Mortar Application	Natural Lime Mortar Grade
General solid brick and stone walls, parapets and lintels	Medium mortar
	Made with NHL3.5 lime
Above roofline, below DPC incl. copings and cappings, earth	Strong mortar
retaining walls	Made with NHL5 lime

The correct specification for any mortar should consider the structural requirements, the nature and condition of the background, site exposure, the time of the year and type of finish required. Less porous masonry units and harsh climates require greater mortar strength.

Surface Preparation

Before pointing or building, clean and remove all dust and loose material from joints and masonry, and adequately dampen dry on high suction surfaces.

How to Mix

Slowly add 25 kg of Lime Green Natural mortar into a drum mixer. Add only 4 to 5 litres of clean water. Pour the water in slowly as the product mixes, using just enough to achieve the correct workability. Mix for 3 to 10 min. Lime Green mortars may be reworked up to 8hrs. Please contact us for further information.

How to Apply

Pointing and building mortars should be finished the same day or the following day in cooler periods. Lime mortars require longer curing times than cement, but the methods and principles of application are similar. When pointing or laying hard impervious masonry and / or during damp cool weather lime mortars may take a few weeks before being fully able to resist frosts. Do not use in temperatures less than 5 °C or over 30°C.

