



Sample image



Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO ₂ EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
0,18% Code : W1 (< 0,4%)	0,28% Complies (< 1,5%)	Longitudinal 49,6 MPA Transverse 39,4 MPA	S1	T1	Fullfil < 0,6%

1— ROOF SLATE

Dark grey natural Spanish slate -250mm x 500mm



Sample

2— TIMBER CLADDING (HIGH LEVEL TO GABLES)

Black feather-edged Siberian Larch, laid horizontally